

SKF Bearing Grease

Extreme pressure grease

LGEP 1

SKF LGEP 1 is a high viscosity, low consistency mineral oil based grease, using a lithium-calcium thickener. It is extremely suitable for the lubrication of large bearings subjected to high loads and low speeds. LGEP 1 has been developed to deliver extended maintenance intervals while minimizing downtime.

- Excellent mechanical stability
- Very good protection against fretting and wear
- Good flow at low starting temperature
- Good flow properties that enable easy replenishment within the bearing design
- Low friction characteristics that help to maintain low operating temperatures
- Excellent water resistance and corrosion protection
- · Good pumpability

Applications


- Wind turbine main shaft bearings
- Large bearing applications
- Heavy industrial applications
- Centralized lubrication systems





Available pack sizes	
Packsize	Designation
18 kg pail	LGEP 1/18





Technical data			
Designation	LGEP 1/(pack size)		
DIN 51825 code	KP1K-20	Corrosion protection	
NLGI consistency class	1	Emcor: – standard ISO 11007 – water washout test	0–0 0–0
Thickener	Lithium-Calcium	– water washout test – salt water test (1% NaCl)	0-0
Colour	Beige	Water resistance	1 max.
Base oil type	Mineral	DIN 51 807/1, 3 hrs at 90 °C	
Operating temperature range	–20 to +120 °C (–4 to +248 °F)	Oil separation	I max.
Dropping point DIN ISO 2176	170 °C min. (338 °F min)	DIN 51 817, 7 days at 40 °C, static, %	1–5
Base oil viscosity 40 °C, mm²/s 100 °C, mm²/s	400 25	Lubrication ability R2F, running test B at 120 °C	Pass at 80 °C (176 °F)
Penetration DIN ISO 2137 60 strokes, 10-1 mm	310–340	Copper corrosion DIN 51 811, 120 °C Rolling bearing grease life ROF test, L ₅₀ life at 10 000 r/min., hrs	1 max.
100 000 strokes, 10 ⁻¹ mm	+50 max.		1 000 min. at 100 °C (212 °F)
Mechanical stability Roll stability, 50 hrs at 80 °C, 10 ⁻¹ mm	+50 max.	EP performance Wear scar DIN 51350/5, 1 400 N, mm 4-ball test, welding load DIN 51350/4. N	1.8 max. 3400 min.
These characteristics represent typical values.		4-ball test, welding load DIN 51350/4. N	3400 min.



Advanced tool for grease selection and relubrication calculation

LubeSelect for SKF greases

Selecting a suitable grease for a particular bearing is a crucial step if the bearing is to meet design expectations in its application. SKF knowledge about bearing lubrication has been encapsulated into a computer program that can be consulted at skf.com/lubeselect

LubeSelect for SKF greases provides you a user friendly tool to select the right grease and suggest frequency and quantity, while taking into account the particular conditions of your application. General guidelines for typical greases for different applications are also available.



Scan or click the QR code, or go to skf.com/lubeselect

skf.com | skf.com/lubrication | skf.com/mapro

- ® SKF is a registered trademark of the SKF Group.
- © SKF Group 2024. All rights reserved. Please note that this publication may not be copied or distributed, in whole or in part, unless prior written permission is granted.

Every care has been taken to ensure the accuracy of the information contained in this publication, but no liability can be accepted for any loss or damage whether direct, indirect or consequential arising out of the use of the information contained herein.

PUB MP/P8 19140/4 EN · March 2024